

10/518757

DT Dec'd PCT/PTO 21 DEC 2004

SMC 60600

APPLICANTS

AVECIA LIMITED

TITLE

DISAZO DYES AND INK JET INKS CONTAINING THEM

DISAZO DYES AND INK JET INKS CONTAINING THEM

This present invention relates to compounds and their salts, to compositions containing such compounds and their use in ink jet printing ("IJP"), to ink jet printer
5 cartridges and to ink jet printing processes.

IJP is a non-impact printing technique in which droplets of coloured liquids are ejected through a fine nozzle onto a substrate without bringing the nozzle into contact with the substrate.

IJP is a relatively inexpensive way of printing multicolour images, for example
10 pictures obtained from digital sources such as electronic cameras, scanners and the Internet. The use of ink jet printers to print colour images in the home or office environment is now becoming commonplace. However IJP has a big disadvantage compared to conventional silver halide photography in that the resultant images fade in ordinary daylight. Thus, there is a need to improve the light-fastness properties of prints
15 to prevent images fading or vanishing, or becoming discoloured over time.

In addition, there are many demanding performance requirements for colorants and inks used in IJP. For example sharp, non-feathered images having good water-fastness and optical density are required. The inks are required to dry quickly when applied to a substrate to prevent smudging, but they should not form a crust over the tip
20 of an ink jet nozzle which stops the printer from working effectively. The inks should also be stable to storage over time without decomposing by forming a precipitate which could block the fine nozzle. Ideally the inks should also possess good humidity and ozone fastness, have a high tinctorial strength and be bright.

The choice of a colorant in ink jet systems is critical to image quality and fastness.
25 The colorants should also have a high degree of light-fastness after printing onto a substrate. For aqueous inks, the colorants need to be sufficiently soluble in water to prepare a solution that is capable of producing adequate density on the substrate and be stable for extended periods of storage without precipitation.


GB 2036780 describes certain yellow disazo dyes for the conventional dyeing of
30 cellulose-containing materials. The dyes comprise two azo components linked by a 1,3,5-triazine (cyanuric) moiety, where one of the azo components is a disulpho-naphthyl group and the other comprises two phenyl groups.

US 5519121 discloses certain cyanuric-linked disazo dyestuffs in printing inks for textiles and paper where one terminal component of the molecule comprises a disulpho-naphthyl group and the other terminal component comprises a sulphonated phenyl group.
35

EP 468647 discloses certain cyanuric-linked disazo yellow dyestuffs for use in inks where both terminal groups independently comprise phenyl or naphthyl, with the proviso that there is at least one carboxylic acid (or thiocarboxylic acid) on a terminal component.

Surprisingly it has been found that compounds of the present invention are excellent colorants for ink jet printing inks.

According to the present invention there is provided a compound of Formula (1):



Formula (1)

wherein:

- A^1 and A^2 are each independently optionally substituted phenyl or naphthyl;
 each Q independently is optionally substituted phenylene;
 each R^1 independently is H or optionally substituted alkyl;
 R^2 is H or optionally substituted alkyl; and
 R^3 is alkyl carrying a sulpho group;

provided that the compound of Formula (1) carries at least one carboxylic acid group; and
 provided that the compound of Formula (1) is not a compound of Formula (2) or a salt thereof:



Formula (2)

wherein:

- m is 1 or 2;
 n is 1 or 2; and
 x is 2 to 4.

In one embodiment of the invention, A^1 and A^2 are the same as each other.

In a further embodiment of the invention, A^1 and A^2 are different from each other.

In a preferred embodiment, one of A^1 and A^2 is optionally substituted naphthyl and the other is optionally substituted phenyl.

In another preferred embodiment, one of A^1 and A^2 carries at least one carboxylic acid group and the other is free from carboxylic acid groups.

In compounds of Formula (2) m , n and x are preferably 2.

Preferred salts are alkali metal salts (especially lithium, sodium and potassium salts), ammonium and substituted ammonium salts and mixtures thereof. Especially preferred salts are sodium, potassium and lithium salts, salts with ammonia and volatile


amines and mixtures thereof. The lithium salts have good solubility, forming particularly storage stable inks with low toxicity and a low tendency to block ink jet nozzles.

The compounds may be converted into a desired salt using known techniques. For example, an alkali metal salt of a compound may be converted into the ammonium or substituted ammonia salt by dissolving an alkali metal salt of the compound in water, acidifying with a mineral acid and adjusting the pH of the solution to pH 9 to 9.5 with ammonia or the amine and removing the alkali metal cations by dialysis or by use of an ion exchange resin.

Examples of amines which may be used to form such salts include methylamine, dimethylamine, trimethylamine, ethylamine, n-propylamine, iso-propylamine, n-butylamine, iso-butylamine, sec-butylamine, tert-butylamine, piperidine, pyridine, morpholine, allylamine, diethylamine, triethylamine, tetramethylamine and mixtures thereof. It is not essential that the dyes are completely in the form of the ammonium salt or substituted ammonium salt and mixed alkali metal and either ammonium salt or substituted ammonium salt are effective, especially those in which at least 50% of the cations are ammonium or substituted ammonium ions.

The above compounds are preferably yellow dyes.

Compounds of Formula (1) may be prepared by condensing an amine of formula HNR^2R^3 with a compound of the Formula (3):



Formula (3)

wherein:

X is a labile atom or group; and

A¹, A², R¹, Q, R² and R³ are as hereinbefore defined.

Preferably X is halo (especially Cl or F).

The condensation is preferably performed in an aqueous medium, more preferably in water. A pH above 7 is preferred because an alkaline pH removes any HX produced during the course of the condensation.

The condensation is preferably performed at a temperature of 5 to 110°C.

The compound of Formula (3) may be prepared by condensing one equivalent of s-triazine carrying three X groups (e.g. cyanuric chloride) with two amines, one of which is of formula $\text{A}^1\text{-N=N-Q-NHR}^1$ and the other of formula $\text{A}^2\text{-N=N-Q-NHR}^1$, wherein X, A¹, A², Q and R¹ are as hereinbefore defined. Preferred condensation considerations are as described above.

The amines of formula $A^1-N=N-Q-NHR^1$ and $A^2-N=N-Q-NHR^1$ may be prepared by diazotising amines of formula A^1-NH_2 and A^2-NH_2 respectively and coupling the resultant diazonium salt with compounds of formula $H-Q-NHR^1$, wherein A^1 , A^2 , Q and R^1 are as hereinbefore defined. Typical diazotisation conditions are those usually employed in the
5 dyestuff art, e.g. employing a temperature below $5^\circ C$, water, dilute mineral acid and sodium nitrate as diazotising agent.

Alternative methods of preparing compounds of Formula (1) may also be used. For example, the amine NHR^2R^3 may be condensed with cyanuric chloride followed by condensation with the amine or amines of formula $A^1-N=N-Q-NR^1H$ and $A^2-N=N-Q-NR^1H$
10 (wherein R^1 , R^2 , R^3 , Q , A^1 and A^2 are as hereinbefore defined).

According to a second aspect of the present invention there is provided a composition comprising a compound according to the first aspect of the invention, or a salt thereof, and a liquid medium. The composition preferably comprises:

(a) from 0.01 to 30 parts of a compound of Formula (1), or salt thereof, as
15 hereinbefore defined; and

(b) from 70 to 99.99 parts of a liquid medium;

wherein all parts are by weight and the number of parts of (a)+(b)=100.

Preferred liquid media include water or a mixture of water and one or more organic solvents.

20 When the liquid medium comprises a mixture of water and organic solvent, the weight ratio of water to organic solvent is preferably from 99:1 to 1:99, more preferably from 99:1 to 50:50 and especially from 95:5 to 80:20.

It is preferred that any organic solvent present in the mixture of water and organic solvent is water-miscible. Preferred water-miscible organic solvents include C_{1-6} -alkanols, preferably methanol, ethanol, n-propanol, isopropanol, n-butanol, sec-butanol, tert-butanol, n-pentanol, cyclopentanol and cyclohexanol; linear amides, preferably dimethylformamide or dimethylacetamide; ketones and ketone-alcohols, preferably acetone, methyl ether ketone, cyclohexanone and diacetone alcohol; water-miscible ethers, preferably tetrahydrofuran and dioxane; diols, preferably diols having from 2 to 12 carbon atoms, for example pentane-1,5-
25 diol, ethylene glycol, propylene glycol, butylene glycol, pentylene glycol, hexylene glycol and thiodiglycol and oligo- and poly-alkyleneglycols, preferably diethylene glycol, triethylene glycol, polyethylene glycol and polypropylene glycol; triols, preferably glycerol and 1,2,6-hexanetriol; mono- C_{1-4} -alkyl ethers of diols, preferably mono- C_{1-4} -alkyl ethers of diols having 2 to 12 carbon atoms, especially 2-methoxyethanol, 2-(2-methoxyethoxy)ethanol, 2-(2-ethoxyethoxy)-ethanol, 2-[2-(2-methoxyethoxy)ethoxy]ethanol, 2-[2-(2-ethoxyethoxy)-ethoxy]-ethanol and ethyleneglycol monoallylether; cyclic amides, preferably 2-pyrrolidone, N-methyl-2-pyrrolidone, N-ethyl-2-pyrrolidone, caprolactam and 1,3-dimethylimidazolidone; cyclic esters, preferably caprolactone; sulfoxides, preferably dimethyl sulfoxide and

sulpholane. Preferably the liquid medium comprises water and 2 or more, especially from 2 to 8, water-soluble organic solvents.

Especially preferred water-miscible organic solvents are cyclic amides, especially 2-pyrrolidone, N-methyl-pyrrolidone and N-ethyl-pyrrolidone; diols, especially 1,5-pentane diol, ethyleneglycol, thiodiglycol, diethyleneglycol and triethyleneglycol; and mono- C₁₋₄-alkyl and C₁₋₄-alkyl ethers of diols, more preferably mono- C₁₋₄-alkyl ethers of diols having 2 to 12 carbon atoms, especially 2-methoxy-2-ethoxy-2-ethoxyethanol.

The pH of the composition is preferably from 4 to 11, more preferably from 7 to 10.

The viscosity of the composition at 25°C is preferably less than 50cP, more preferably less than 20 cP and especially less than 5cP.

When the composition according to the invention is used as ink jet printing compositions, the composition preferably has a concentration of halide ions of less than 500 parts per million, more preferably less than 100 parts per million. It is especially preferred that the composition has less than 100, more preferably less than 50 parts per million of divalent and trivalent metals, wherein parts refer to parts by weight relative to the total weight of the composition. We have found that purifying the compositions to reduce the concentration of these undesirable ions reduces nozzle blockage in ink jet printing heads, particularly in thermal ink jet printers.

The compounds of Formula (1) may be used as the sole colorant in the compositions because of their attractive yellow shade. However, if desired, one may combine the present compounds with one or more further yellow colorants if a slightly different shade is required for a particular end use. The further colorants are preferably dyes. When further colorants are included in the composition these are preferably selected from but not limited to yellow colorants such as C.I.Direct Yellow 142; C.I.Direct Yellow 132; C.I.Direct Yellow 86; C.I.Direct Yellow 85; C.I. Direct Yellow 173; and C.I.Acid Yellow 23 and combinations thereof.

The composition according to this aspect of the present invention may also contain additional components conventionally used in ink jet printing inks, for example viscosity and surface tension modifiers, corrosion inhibitors, biocides, kogation reducing additives and surfactants which may be ionic or non-ionic.

A third aspect of the present invention provides a process for printing an image on a substrate comprising applying thereto a composition according to the second aspect of the present invention.

The process for printing the image preferably is carried out by means of an ink jet printer. The ink jet printer preferably applies the composition to the substrate in the form of droplets which are ejected through a small orifice onto the substrate. Preferred ink jet printers are piezoelectric ink jet printers and thermal ink jet printers. In thermal ink jet printers, programmed pulses of heat are applied to the composition in a reservoir by means of a resistor adjacent to the orifice, thereby causing the composition to be ejected in the

form of small droplets directed towards the substrate during relative movement between the substrate and the orifice. In piezoelectric ink jet printers the oscillation of a small crystal causes ejection of the composition from the orifice.

The substrate is preferably paper, plastic, a textile, metal or glass, more preferably paper, an overhead projector slide or a textile material, especially paper.

Preferred papers are plain or treated papers which may have an acid, alkaline or neutral character. Examples of commercially available treated papers include HP Premium Coated Paper, HP Photopaper™ (both available from Hewlett Packard Inc.); Stylus™ Pro 720 dpi Coated Paper, Epson Photo Quality™ Glossy Film, Epson Photo Quality™ Glossy Paper (all available from Seiko Epson Corp.); Canon HR 101 High Resolution™ Paper, Canon GP 201 Glossy™ Paper, Canon HG 101 and HG201 High Gloss™ Film, Canon PR101 (all available from Canon); Kodak Premium™ Photopaper, Kodak Premium™ InkJetpaper (available from Kodak); Konica Inkjet Paper QP™ Professional Photo Glossy, Konica Inkjet Paper QP™ Professional Photo 2-sided Glossy, Konica Inkjet Paper QP™ Premium Photo Glossy, Konica Inkjet Paper QP™ Premium Photo Silky (available from Konica).

A fourth aspect of the present invention provides an ink jet printer cartridge, optionally refillable, comprising one or more chambers and a composition, wherein the composition is present in at least one of the chambers and the composition is as defined in the second aspect of the invention.


A fifth aspect of the present invention provides separately a paper, an overhead projector slide or a textile material printed with a composition according to the present invention or by means of a process according to the third aspect of the present invention.

The invention is further illustrated by the following Examples in which all parts and percentages are by weight unless otherwise stated.

EXAMPLES

Example 1

5 Preparation of Dye 1:



Dye 1

10 Stage (1) Preparation of Monoazo(1).

3-sulpho-aniline (17.3g) was dissolved in water (400ml) at neutral pH, sodium nitrite (6.9g) was added and the mixture was cooled to 0-5° C. Concentrated hydrochloric acid (30ml) was added, and the mixture was stirred until diazotisation was complete. Excess nitrous acid was destroyed with sulphamic acid, and a solution of o-anisidine- ω -methanesulphonic acid (OAMS) (32g), dissolved in water (300 ml) at neutral pH, was added to the diazonium salt solution. The pH was increased 7 with sodium carbonate, and the reaction mixture was stirred overnight at room temperature. The resultant precipitate was filtered off and the filter cake was resuspended in water (800ml), sodium hydroxide solution (20 ml) was added, and the mixture was heated to 60°C. When reaction was complete the mixture was cooled to room temperature, the pH was adjusted to pH 4 and sodium chloride solution (10% w/v) was added to precipitate the product ("Monoazo(1)") which was isolated by filtration.

25 Stage (2) Preparation of Monoazo(2).

5-amino-isophthalic acid (18g) was dissolved in water (200ml), and the pH was adjusted to pH7 with sodium hydroxide. Sodium nitrite (6.9g) was added and the mixture was stirred for 5 minutes, then cooled to 0-5° C. Concentrated HCl (35ml) was added slowly, and stirring continued at 0-5°C until diazotisation was complete. Excess nitrous was destroyed with sulphamic acid. A solution of aniline- ω -methanesulphonic acid (AMS) (32g) in water (300 ml) at neutral pH was added to the diazonium salt solution, and the

pH was increased to pH7 with sodium carbonate. The mixture was stirred overnight at room temperature, whereupon the precipitated product was filtered off, and resuspended in water (800ml), and the pH adjusted to pH10 with sodium hydroxide. The mixture was heated mixture to 60-70°C, and when hydrolysis was complete cooled to room temperature, whereupon the pH was adjusted to pH4. A solution of sodium chloride (10% w/v) was added to precipitate the product ("Monoazo(2)") which was isolated by filtration.

Stage (3) Preparation of Title Dye

Monoazo(1) (0.2mol) was dissolved in water at pH7, calsolene oil (2drops) was added and the solution was cooled to 0-5° C. Cyanuric chloride (4g) added over 10 minutes, during which time the pH was maintained pH 6.5-7 with sodium carbonate solution. The mixture was stirred until reaction was complete, then allowed to warm to room temperature. The pH was adjusted pH7 and the mixture was stirred 1 hour.

A solution of Monoazo(2) (0.2mol) in water (100ml) was added to the above solution, and the pH was maintained at pH7 for 24 hours. When reaction was complete the pH was lowered to pH4 and sodium chloride (20%w/v) was added to precipitate the product, which was isolated by filtration and washed with saturated brine solution. The solid was resuspended in water (500ml) and 2-aminoethanesulphonic acid (0.6mol) was added. The pH was adjusted to pH 9.5 and the mixture heated to 70° C for 6 hours, and subsequently cooled to room temperature and adjusted to pH3 whereupon the product precipitated completely out of solution and was isolated by filtration. The solution was then dialysed using Visking™ tubing (<50 μScm^{-1}) to low conductivity, screened through a cascade of filters (GF/A, GF/D, 0.45 μm) and dried in the oven to give the title product.

Examples 2 to 10

The method of Example 1 was repeated, except that in place of 3-sulfoaniline in Stage (1) there was used the amine indicated in column A¹ of Table 1, in place of OAMS in Stage (1) there was used the compound indicated in column Q¹ of Table 1, and in place of AMS in Stage (2) there was used the compound indicated in column Q² of Table (1), wherein the compounds in columns Q¹ and Q² are as defined below:

OAMS = o-anisidine- ω -methanesulphonate

MAMS = m-anisidine- ω -methanesulphonate

AMS = aniline- ω -methanesulphonate

MT = m-toluidine









MEA = m-ethylaniline.

In Example 2 only, 2-(methylamino)ethane sulphonic acid was used in place of 2-aminoethane sulphonic acid in Stage (3).

The resultant dye structure in each case is shown in the far right hand column of Table 1.

Table 1

Example Number	A ¹	Q ¹	Q ²	Final structure
2		AMS	AMS	
3		MAMS	MT	
4		MAMS	MT	
5		OAMS	MT	
6		MEA	MT	

7		MT	MT	
8		MAMS	MEA	
9		MT	AMS	
10		MAMS	AMS	

Example 11 - Ink formulations and testing

Ink jet printing inks were prepared according to the following formulation wherein Dye was the dye from Examples 1 to 10 above:

5	2-Pyrrolidone	5 parts
	Thiodiglycol	5 parts
	Surfynol™ 465	1 part (from Air Products Inc., USA)
	Dye	3 parts
	Water	86 parts.

10 The inks containing Dyes 1 to 10 ("Inks 1 to 10") were printed onto a range of proprietary media using an Epson Stylus™ 880 piezoelectric ink jet printer, and gave prints of excellent light and ozone fastness.

15 Further inks may be prepared in a similar fashion according to the formulations shown in Tables (I) and (II) wherein the dye described in the first column is the dye made in the above examples, and wherein numbers quoted in the second column onwards refer to the number of parts of the relevant ingredient and all parts are by weight. The inks may be applied to paper by thermal or piezo ink jet printing.

The following abbreviations are used in Table (I) and (II):

20	PG = propylene glycol
	DEG = diethylene glycol
	NMP = N-methyl pyrrolidone
	DMK = dimethylketone
	IPA = isopropanol
	MEOH = methanol
	2P = 2-pyrrolidone
25	MIBK = methylisobutyl ketone
	P12 = propane-1,2-diol
	BDL = butane-2,3-diol
	CET= cetyl ammonium bromide
	PHO = Na ₂ HPO ₄ and
30	TBT = tertiary butanol
	TDG = thiodiglycol

TABLE I

Dye	Dye Content	Water	PG	DEG	NMP	DMK	NaOH	Na Stearate	IPA	MEOH	2P	MIBK
1	2.0	80	5		6	4					5	
2	3.0	90		5	5		0.2			5	1	1
3	10.0	85	3		3	3						5
4	2.1	91		8								1
5	3.1	86	5					0.2	4			5
6	1.1	81			9		0.5				9	
7	2.5	60	4	15	3	3			6	10	5	4
8	5	65		20					10			
9	2.4	75	5	4		5				6		5
10	4.1	80	3	5	2	10		0.3				
1	3.2	65		5	4	6			5	4	6	5
2	5.1	96								4		
3	10.8	90	5						5			
4	10.0	80	2	6	2	5			1		4	
5	1.8	80		5							15	
6	2.6	84			11						5	
7	3.3	80	2			10				2		6
8	12.0	90				7	0.3		3			
9	5.4	69	2	20	2	1					3	3
10	6.0	91			4						5	

TABLE II

Dye	Dye Content	Water	PG	DEG	NMP	CET	TBT	TDG	BDL	PHO	2P	PI2
1	3.0	80	15			0.2					5	
2	9.0	90		5						1.2		5
3	1.5	85	5	5		0.15	5.0	0.2				
4	2.5	90		6	4					0.12		
5	3.1	82	4	8		0.3						6
6	0.9	85		10					5	0.2		
7	8.0	90		5	5			0.3				
8	4.0	70		10	4				1		4	11
9	2.2	75	4	10	3				2		6	
10	10.0	91			6						3	
1	9.0	76		9	7		3.0			0.95	5	
2	5.0	78	5	11							6	
3	5.4	86			7						7	
4	2.1	70	5	5	5	0.1	0.2	0.1	5	0.1	5	
5	2.0	90		10								
6	2	88						10				
7	5	78			5			12			5	
8	8	70	2		8			15			5	
9	10	80						8			12	
10	10	80		10								